



COPY RIGHT

2018 IJIEMR. Personal use of this material is permitted. Permission from IJIEMR must be obtained for all other uses, in any current or future media, including reprinting/republishing this material for advertising or promotional purposes, creating new collective works, for resale or redistribution to servers or lists, or reuse of any copyrighted component of this work in other works. No Reprint should be done to this paper, all copy right is authenticated to Paper Authors

IJIEMR Transactions, online available on 25th Oct 2018. Link

[:http://www.ijiemr.org/downloads.php?vol=Volume-07&issue=ISSUE-11](http://www.ijiemr.org/downloads.php?vol=Volume-07&issue=ISSUE-11)

Title: AN EXPERIMENTAL STUDY ON GEOPOLYMER CONCRETE BY REPLACEMENT OF SAND WITH MANUFACTURED SAND AND ITS DURABILITY

Volume 07, Issue 11, Pages: 32–38.

Paper Authors

B.SUNANDA, MR. RAVI SHANKAR

Bharath Institute of Engineering & Technology Hyderabad



USE THIS BARCODE TO ACCESS YOUR ONLINE PAPER

To Secure Your Paper As Per **UGC Guidelines** We Are Providing A Electronic Bar Code

AN EXPERIMENTAL STUDY ON GEOPOLYMER CONCRETE BY REPLACEMENT OF SAND WITH MANUFACTURED SAND AND ITS DURABILITY

B.SUNANDA¹, MR. RAVI SHANKAR²

¹M.Tech (Structural Engineering), Dept Civil Eng, Bharath Institute of Engineering & Technology Hyderabad

²Assistant Professor, Dept Civil Engg, Bharath Institute of Engineering & Technology Hyderabad.

ABSTRACT:-Concrete is the largely common material used for construction all over the world. The demand for concrete as a construction material leads to the raise of demand for Portland cement. Geopolymer is an eco-friendly binding material alternative to ordinary Portland cement. Geopolymer concrete is obtained by mixing the ingredients such as sodium hydroxide solution, sodium silicate solution (NaOH and Na₂SiO₃), or potassium hydroxide, potassium silicate solutions (KOH and K₂SiO₃), fly ash, grounded granulated blast furnace slag (GGBS) and, fine aggregate and coarse aggregate and cured suitably. The blend of sodium hydroxide solution and sodium silicate solution is termed as alkaline liquid. This study presents research deals with Geopolymer concrete by replacing of fine aggregate material with using the Msand. Complete 100% replacement of natural sand with Manufactured sand and compare the results with GPC natural sand and GPC with Msand and its durability. When exposed to sulphate, and acidic environment and assessment were made with normal Ordinary Portland Cement (OPC) concrete. In total four tests were conducted to determine acid and sulphate resistance of geopolymer concrete with Msand. The tests involved concentration for a period of 30 to 60 days into 5% solution of sodium sulphate, 5% solution of magnesium sulphate, 5% solution of sulphuric acid and 5% solution of phosphoric acid. The progression of weight loss and compressive strength loss were studied. The most major degradation of compressive strength and weight were determined in 5% of acid solution. The minimum strength dissimilarity and weight loss were found in the 5% of sulphate solution. The Ordinary PC concrete deteriorated more in acid as well as in sulphate solution in compared with geopolymer concrete, thus geopolymer concrete is more durable than the OPC concrete.

Keywords: Binding material, GPC, Manufactured sand, degradation, deteriorated

I INTRODUCTION

Concrete is the utmost versatile material of construction far and wide. The usage of concrete were increasing steadily. The cement industry is the second largest producer of the greenhouse gas. Manufacturing process of cement demand in discharge of huge quantity of greenhouse

gases like Carbon dioxide into atmosphere. For the fabrication of 1 tone of cement produce approximately 1 tone of carbon dioxide. Burning of lime stone, clay and other materials @ 1500°C produces of carbon dioxide. Concrete is the substance of possibility for a change of request

such as housing, bridges, highway pavements, industrial structures, water-carrying and retaining structures, etc.

GEO- POLYMER:-Davidovits (1978) father of geo-polymer .Geo-polymer is a advanced family of cementations materials that is way more environmental good natured due to its less emission of CO₂ gas and energy consumption. Geo-polymers can be used as cementations material that utilize high siliceous materials like fly ash, Ground Granulated Blast furnace slag(GGBS), Silica Fume (SF),Rice Husk Ash (RHA), and Metakaolin (MK) for binding which can produce an eco-friendly material. These materials available with less cost and only for transportation it costs. By expanding the Molarities the strength of GPC were also increases. Geo-polymer is an intermix result ofaluminum and silicon. It is manufactured by geochemistry process.Alkaline solution is worn as the binding material for geo-polymer concrete. Alkaline solution is made using sodium hydroxide (NaOH) and sodium silicate (NasiO₃) solutions. Fly ash based geo-polymers use fly ash as the substance which react as source of silicon and aluminum for reaction by an alkali to make silicon and aluminum atoms to form geo-polymer paste. Geo-polymer materials are generally low density due to the active of micro sized and Nano sized pores within the end products.

MATERIALS USED FORGPC:-

1. Fly ash (Class F):-The greater part of fly ash used, in a consequence from the burning of pulverized coal to generate electricity at power stations. Fly-ash mainly contains silica, alumina and minor amounts of oxides such as iron (Fe), sodium (Na), calcium (Ca), magnesium (Mg) and potassium (K). But major chemical constituents in class-F fly

ash are alumina and silica, combined occupies supplementary than 90% of fly ash and low in calcium. Where as in class F fly ash low in calcium. The class-F fly ash used in our work is secure from National Thermal Power Project (NTPC) Vijayawada, ANDHRA PRADESH.

2. GGBS (ground granulated blast-furnace slag):-GGBS is a consequence from the producing of iron. Molten slag is drain off from the blast furnace through out the production of molten iron. If it is cooled quickly, the powdered material has inactive pneumatic properties. These utilize at a temperature of about 1,500 degrees centigrade and are fed with a attentive manage mixture of iron-ore, coke and limestone. The iron ore is minimized to iron and the endure materials form a slag that floats on the surface of the iron. This is separated from separate hopper and collected in the cyclone filters. In this operation the temperature used to be reduced and moved to storage silo from here the transportation is carried. This slag is frequently drained off as a molten liquid and it is to be used for the production of GGBS.

RAW MATERIALS:-

1. AlkalinesolutionA combination of the sodium hydroxide and sodium silicate solutions was used as the alkaline liquid to activate Fly ash and GGBS. Sodium hydroxide pellets and sodium silicate solution used in this study are shown. Sodium based solutions were chosen because they were cheaper than Potassium based solutions. The sodium hydroxide solids were either a technical grade in flake or pellets. The sodium hydroxide flakes were obtained from SREE chemical agencies gollapudi, Vijayawada and fusion chemicals & products

pvt.Ltd.Telangana.

2. Manufactured sand: Manufactured sand is used as secondary material of fine aggregate and which is collected from stone crusher. Manufactured sand has not been used much in India for that basis that normally squeeze sand is blistering, badly graded, rough textured, contain excess of dust hence they result in production of poor concrete for the given design frame work. In this operation stone is crushed in 5 dissimilar crusher's stages to get M-sand.

OBJECTIVE OF THE STUDY:-

1. To develop the proper blend proportion for geo-polymer concrete and renewal of natural sand with M-sand in geo-polymer concrete.
2. To study the behavior of GPC and to know compressive strength and split tensile strength GPC made with M-sand
3. Concrete cubes, cylinders specimens made with Fly ash and GGBS.
4. To evaluate the different strength and durability properties of geo-polymer concrete mixture replaced with Manufactured sand
5. Different Types of Durability tests were to be done and compared with OPC

II LITERATURE REVIEW

- The mixture of fly ash (FA) and ground granulated blast-furnace slag (GGBS) is produces high-strength geo-polymer concrete
- Low calcium Class F (ASTM) dry fly ash is more preferable for the geo-polymer concrete due to affluent in silicon and aluminum

,Compressive strength of the geo-polymer concrete is higher while comparing with ordinary Portland cement

- Increasing the percentage of fine quality in concrete by adding together M-sand reduces the porosity.
- By adding M-sand to concrete enlarge the compressive strength.
- The addition of basalt fiber can considerably develop deformation and energy combination capacities of geo-polymer concrete.
- Use of steel fibers in different volume portion in concrete can increase the ductility factor and load carrying capacity of specimens.
- Steam curing is very efficient for geo-polymer concrete specimens.
- Strength of GPC increases if curing time is improved
- Geo-polymer concrete has high resistance to acid attacks.
- Geo-polymer concrete resist heat for long time.
- Curing temperature and nature of alkaline solution, Alkaline activator concentration, are the most significant stricture necessary for optimization of Geo-polymer mortar specimens of elevated temperature as they affects physical-mechanical properties and microstructure at superior temperature.

On the source of accessible literature on geo-polymer concrete for the most part of the works done in the past have been by means of only Fly ash as a source material. Very few numbers of works has been done

on Fly ash and GGBS- based geo-polymer concrete. From the literature survey, replacement of natural sand with M-sand in to the geo-polymer concrete will improve the properties of GPC.

III METHODOLOGY

MANUFACTURE OF GEOPOLYMER CONCRETE:-

Davidovits (2002) recommended that it is preferable to mix the sodium silicate solution and sodium hydroxide solution collectively at least one day before adding the solution to the solid constituents. Fly ash and GGBS- based geo-polymer concrete was dark in color, and concrete was cohesive. Segregation and bleeding were occurred when water satisfied in the mixture is high. From the initial work, it was determined to observe the following standard process of mixing in all further studies.

- i. Mix sodium hydroxide solution and sodium silicate solution jointly at least one day previous to adding the liquid to the dry materials.
- ii. The fly ash, GGBS was sieved from 90 Microns sieve without any lumps.
- iii. The aggregates have to be arranged in soaked-surface dry condition.
- iv. Mix all dry materials in the pan mixer for about three minutes. The alkaline liquid has to be varied with the super plasticizer and the additional water, if any Add the liquid constituent of the mixture at the end of dry mixing, and maintain the wet mixing for another four minutes.

COST ANALYSIS:-Cement has a very efficient moving and transportation system in our country which makes its transportation cost less. GGBS and coal ash currently doesn't have such a system. To regulate this end product, the transportation of these materials is said to be in the similar behavior as cement. Standard contents accuse from Indian Railway website is measured

for this analysis. Local market price for NaOH and aggregates were considered in this study. The cost per quantity and total cost is mentioned in Table 3.10. Only fly ash-GGBS based concrete are used for this study.

Materials	cost
GGBS	1.5
Fly Ash	1
Coarse Aggregate 0.43	0.43
Fine Aggregate	1.55
Water	0.1
NaOH	80
Sodium Silicate	10

The total cost of geo-polymer concrete (Rs 4153.38) for cubic meter . The cost of OPC concrete exist taken as of ready mix plant cost since now a days for industrial or domestic construction were made by using RMC plants. It is easy and 20% less than OPC based concrete (Rs 3300). This concentrated cost is mostly due to the assumptions made for the transportation of coal ash, GGBS and sodium silicate. If we are not considering the ready mix cost and if we takenversine material means it costs around (Rs 5500.00) based up on distance the cost of materials were changed. The transportation cost plays a major roll.

IV RESULT ANALYSIS

1. Compressive strength after Alkaline test

No. of Days	OPC concrete (%)	Geopolymer concrete (%)
0 days	41.3	64.7
30 days	35.3	61.2
60 days	31.6	56.3

2. Compressive strength after sulphate attack test

No. of Days	OPC concrete (%)	Geopolymer concrete (%)
0 days	41.3	64.7
30 days	36.3	60.3
60 days	31.1	58.07

3. Compressive strength after chloride attack test

No. of Days	OPC concrete (%)	Geopolymer concrete (%)
0 days	41.3	64.7
30 days	32.13	59.6
60 days	30.6	57.3

4. Compressive strength after Acid resistance test

No. of Days	OPC concrete (%)	Geopolymer concrete (%)
0 days	41.3	64.7
30 days	34.6	58.3
60 days	30.8	55.3

V CONCLUSION

The research reported here in comprised experimental study on the performance of geo-polymer concrete by alternative of natural river sand with manufacturing sand and strength of fly ash and GGBS- based geo-polymer concrete specimens. Low calcium (ASTM Class F) dry fly ash obtained from the thermal power plant vijayawada, Andhra pradesh was used as the

basis material to compose geo-polymer concrete. complete replacement of cement were taken in the mix design using 50% GGBS and 50% Fly ash based. Addition of GGBS increases the strength of the geo-polymer concrete. M-sand is used in this study by complete replacement of fine aggregate. Sodium silicate solution and sodium hydroxide solution were mixed to form alkaline solution. This alkaline solution have to be prepared one day before mixing with dry materials. The silicon and aluminum in fly ash reacted with alkaline solution to the form geo-polymer paste that bound the loose aggregate and un-reacted materials to produce the geo-polymer concrete. Geo-polymer Concrete based on fly ash gain a very high compressive strength in the first few hours of alkali activation (40-50 MPa after 24 hours) The aggregate consisted of coarse aggregate of maximum size 20 mm and fine aggregate conforming to zone II. The mix proportion and manufacturing process used to make the geo-polymer concrete were based on the earlier studies available on geo-polymer concrete.

Total 70 geo-polymer concrete cubes were made and tested for compressive strength and for durability. In this 12 cylinders and 12 beams are made with Fly ash and GGBS M-sand geo-polymer concrete and 36 more cubes are made with OPC concrete to compare the test results of durability. These cubes, cylinders and beam tested for compressive, flexure and shear behavior of geo-polymer concrete. Test results of these specimens are compared with the test results of M-sand specimens. The cost analysis were considered based upon market price. If we use commercial grade inset of laboratory grade the cost of sodium hydroxide and

sodium silicate were reduced to 25% of actual price. By using M-sand instead of natural sand reduce the cost. The strength variation also more than compared with OPC concrete.

The major conclusion drawn from this research are presented below:

- Geo-polymer concrete in structural applications has led to the total elimination of cement from concrete, which finally becomes “Green Concrete”
- The fly ash, once considered as waste material, has originated significance through Geo-polymer concrete in construction industries and become a valuable material
- The increase in the absorption of sodium hydroxide from 8 M to 12M increased the viscosity and reduced the fresh properties of SCC mix.
- The increase in the NaOH molarity increased the compressive strength of SCGC
- By replacement of natural sand with M-sand reduces the cost of concrete and no side effects
- Geo-polymer concrete can be prepared at comparable cost with OPC based concrete provided transportation system for raw materials is well established.
- While the addition of M-sand improved the loading capacity significantly, the improvement was marginal for ultimate load. The voids were reduced to 20% because M-sand contains dust particles.
- Energy absorption capacity increases in the cylinders and beams with M-sand compared to natural sand.

- Its resistance against sulphate and acid attack makes it suitable to be used for construction in abrasive soils where ground water contains considerable amount of sulphate salts
- The compressive strength increased up to 25% for the durability

REFERENCES

- [1] ACI Committee 440, “State-of-the-art report on fiber reinforced plastic reinforcement for concrete structures”, Report ACI 440R-96, USA: *American Concrete Institute*, 1996.
- [2] Aiello MA, and Ombres L, “Cracking and deformability analysis of reinforced concrete beams strengthened with externally bonded carbon fiber reinforced polymer sheet”, *ASCE Journal of Materials in Civil Engineering*, vol. 16, No. 5, pp.292-399, 2004.
- [3] Akbarzadeh H, and Maghsoudi AA, “Experimental and analytical investigation of reinforced high strength concrete continuous beams strengthened with fiber reinforced polymer”, *Materials and Design*, vol. 31, pp. 1130-1147, 2010.
- [4] Arduini M, and Nanni A, “Behaviour of pre-cracked R. C. beams strengthened with carbon FRP sheets”, *ASCE Journal of Composites for Construction*, vol. 1, No. 2, pp. 63- 70, 1997.
- [5] Ashour AF, El-Refaie SA, and Garrity SW, “Flexural strengthening of RC continuous beams using CFRP laminates”, *Cement and Concrete Composites*, vol. 26, pp. 765-775, 2003.
- [6] Ceroni F, “Experimental performances of RC beams strengthened with FRP materials”, *Construction and Building*

Materials, vol. 24, pp. 1547-1559, 2010.

[7] El-Refaie SA, Ashour AF, and Garrity SW, "Sagging strengthening of continuous reinforced concrete beams using carbon fibre sheets", *The 11th BCA Annual Conference on Higher Education and the Concrete Industry*, Manchester, UK, pp. 281-292, 3-4 July 2001.

[8] El-Refaie SA, Ashour AF, and Garrity SW, "Strengthening of reinforced concrete continuous beams with CFRP composites", *The International Conference on Structural Engineering, Mechanics and Computation*, Cape Town, South Africa, 2-4. , pp.1591-1598, April 2001.

[9] Garden HN, and Hollaway LC, "An experimental study of the influence of plate end anchorage of carbon fibre composite plates used to strengthen reinforced concrete beams", *Composite Structures*, vol. 42, pp. 175-188, 1998.

[10] Grace NF, "Strengthening of negative moment region of reinforced concrete beams using carbon fiber- reinforced polymer strips", *ACI Structural Journal*, vol. 98, No. 3, pp. 347- 358, 2001.

[11] Grace NF, Sayed GA, and Saleh KR, "Strengthening of continuous beams using fibre reinforced polymer laminates", *American Concrete Institute*, Farmington Hills, Mich, pp. 647-657, 1999.

[12] Grace NF, Soliman AK, Abdel-Sayed G, and Saleh KR, "Strengthening of continuous beams using fibre reinforced polymer laminates", *Proceedings of 4th International Symposium on Fibre Reinforced Polymer Reinforcements for Reinforced Concrete Structures*, SP-188, American Concrete Institute, Farmington Hills, Michigan, USA,

pp.647-657, 1999.

[13] Jumaat MZ, Rahman MM, and Rahman MA, "Review on bonding techniques of CFRP in strengthening concrete structures", *International Journal of the Physical Sciences*, vol. 6(15), pp. 3567-3575, 4 August. 2011.

[14] Khalifa A, Tumialan G, Nanni A, and Belarbi A, "Shear Strengthening of Continuous Reinforced Beams Using Externally Bonded Carbon Fiber Reinforced Polymer Sheets", *In: Fourth International Symposium on Fiber Reinforced Polymer Reinforcement for Reinforced Concrete Structures*, Baltimore, MD, American Concrete Institute, pp. 995-1008, November 1999.