



International Journal for Innovative Engineering and Management Research

A Peer Reviewed Open Access International Journal

www.ijiemr.org

COPY RIGHT



ELSEVIER
SSRN

2019IJIEMR. Personal use of this material is permitted. Permission from IJIEMR must be obtained for all other uses, in any current or future media, including reprinting/republishing this material for advertising or promotional purposes, creating new collective works, for resale or redistribution to servers or lists, or reuse of any copyrighted component of this work in other works. No Reprint should be done to this paper, all copy right is authenticated to Paper Authors

IJIEMR Transactions, online available on 9th Dec 2019. Link

[:http://www.ijiemr.org/downloads.php?vol=Volume-08&issue=ISSUE-12](http://www.ijiemr.org/downloads.php?vol=Volume-08&issue=ISSUE-12)

Title **A STUDY OF STRENGTH ASSEMENT OF CONCRETE BY PARTIAL REPLACEMENT CEMENT WITH METAKOLIN AND FLYASH**

Volume 08, Issue 12, Pages: 12-16.

Paper Authors

RAMA KRISHNA MUKESH.GUNDABATTULA, AMISIGADDA SAI NAGA MANIKANTA

KAKINADA INSTITUTE OF TECHNOLOGICAL SCIENCES, RAMACHANDRAPURAM,
ANDHRAPRADESH, INDIA, 533287



USE THIS BARCODE TO ACCESS YOUR ONLINE PAPER

To Secure Your Paper As Per **UGC Guidelines** We Are Providing A Electronic Bar Code

A STUDY OF STRENGTH ASSEMENT OF CONCRETE BY PARTIAL REPLACEMENT CEMENT WITH METAKOLIN AND FLYASH

¹RAMA KRISHNA MUKESH.GUNDBATTULA, ²AMISIGADDA SAI NAGA MANIKANTA

¹M-TECH, DEPT OF CIVIL, KAKINADA INSTITUTE OF TECHNOLOGICAL SCIENCES, RAMACHANDRAPURAM, ANDHRAPRADESH, INDIA, 533287

²ASSOCIATE PROFESSOR, KAKINADA INSTITUTE OF TECHNOLOGICAL SCIENCES, RAMACHANDRAPURAM, ANDHRAPRADESH, INDIA, 533287

ABSTRACT:

Today record takes care of the impacts of mineral admixtures, by partial substitute of concrete, in regards to enhanced efficiency on compressive and also flexural toughness. Speculative job was executed to explore the impact of Meta kaolin as well as Fly ash by partial changing concrete and also maintaining very same water concrete proportion to average concrete and also metakaolin as well as fly ash. In this program we are mosting likely to build 48 dice examples of dimension 150mmx150mmx150mm for various portions of Meta kaolin and also Fly ash with partial substitute of concrete will certainly casted and also evaluated. The concrete blends had 0%, 5%, 10%,15% of Fly ash and also Meta Kaolin, changing concrete partly, so regarding identify the very best percentage, which would certainly offer optimal compressive stamina. It exposes that with 10%Meta kaolin and also Fly ash each partial substitute of concrete were discovered to be most good mixes for spreading of concrete flexural participants. Utilizing the maximum mix percentage providing the very best lead to compressive stamina of dice screening, beam of light samplings will certainly casted as well as checked for their flexural stamina. The measurements of each beam of light will certainly 750mm x150mm x 150mm. The light beams Will evaluated on global screening maker to confirm their flexural toughness after 7days, 28 days of healing with solitary factor tons. The outcomes will certainly compare to the light beams of differing flexural stamina of Plane Cement Concrete, Plane Cement Concrete with Meta kaolin and also Fly ash.

Keywords: SCC, Fibers, carbon fibers, Compacting, Crack, strength, M30 grade.

1. INTRODUCTION:

This current record intended towards power language within the concrete and also concrete organization has partially, concentrated on using much less power extensive products like ash, scoria as well as oxide Fume. Lately some focus has-been provided to the usage of Natural Pozzolans like Meta porcelain clay as a prospective

partial substitute for concrete. Among the diverse methods accustomed boost the strength of concrete, and also to achieve high efficiency concrete, the use of Meta porcelain clay can be a relatively brand-new technique. Meta porcelain clay, or heat-treated clay, can additionally be made use of a Supplementary Cementations Material in

concrete to cut down concrete intake, to prolong strength. Meta porcelain clay minimizes the consistence of concrete. Simple concrete has a truly reduced lastingness, restricted ductility and also little resistance to breaking. Concrete is one amongst the leading typical products utilized in the building and construction service. In the previous couple of years, numerous evaluation as well as alterations has actually been done to provide concrete with wanted attributes. Concrete is that one of the most normally utilized and also functional artefact having high compressive toughness, by enhancements of some Pozzolanic products, the diverse residential properties of concrete specialist, workability, resilience, stamina, resistance to fractures and also permeable will certainly be boosted. The application of Meta porcelain clay as a partial concrete substitute's product in mortar as well as concretes has actually been researched in the last few years, despite of varieties of researches, use Meta porcelain clay remains to be not stylishly in observe. The usage of concrete replacement products essential in creating reduced worth building and construction products. Concrete is that one of the most normally utilized as well as flexible structure product that is primarily accustomed withstand compressive pressures. By enhancement of some pozzolanic products, the various residential or commercial properties of concrete viz., Compressive Strength, Flexural Strength consistence will certainly be boost. The gave evaluation is intended towards learning the buildings like optimal share of Meta porcelain clay and also Fly Ash with partial substitute of concrete, to see the optimal

concrete integrate. The maximum concrete combines made use of to see the compressive, flexural stamina. The research study in addition targets at essential the flexural toughness of the concrete beam of lights sustained the cross sectional measurements, period and also amount of metakaolin as well as flyash utilized as well as compared to real stamina acquired sustained speculative outcomes. The study searchings for can help with designers to understand the efficiency of concrete for flexural toughness as well as compressive toughness.



**Fig.1.1. LIGHTER COLOUR
METAKOLIN**

2. RELATED STUDY:

Considerable research has been done on natural pozzolans, namely on thermally activated ordinary clay and kaolinitic clay. These unpurified materials have often been called "Meta kaolin". Such a product, white or cream in color, purified, thermally activated is called High Reactive Meta kaolin(HRM).High reactive meta kaolin shows high pozzolanic reactivity and reduction in Ca(OH)_2 even as early as one day. It is also observed that the cement paste undergoes distinct densification. The improvement offered by this densification

includes an increase in strength and decrease in permeability. The Meta kaolin using as a cement replacement in concrete countertop mixes, instead of other pozzolans such as silica flume, fly ash to: Boost compressive strength

- Make finishing easier
- Reduce efflorescence
- Maintain color, especially in Other Portland Cement

Fly ash is also known as flue-ash, it is one of the residues generated in combustion, and comprises the fine particles that rise with the flue gases. In an industrial context, fly ash usually refers to ash produced during combustion of coal. Fly ash is the finely divided residue from the combustion of ground or powdered coal which is transported from the fire box by the fuel gases and is subsequently removed from the gas by electrostatic precipitators. During combustion of coal in thermal power plants, the volcanic matter and carbon are burnt off, whereas mineral impurities in the coal such as clay, quartz, feldspar etc., melt and are transported to lower temperature zones, where it is solidifies as spherical particles of glass. Some of this mineral matter agglomerates to form bottom ash, but most of its flies out with the flue gases called fly ash. In India, fly ash was used for the first time in construction of Remand Irrigation Project, Uttar Pradesh in 1962, replacing cement up to about 15%. ASTM broadly classified fly ash into two classes as Class F fly ash: Fly ash normally produced by burning anthracite or bituminous coal, usually has been than 5% CaO. Class F fly

ash has pozzolanic properties only. Class C fly ash: Fly ash normally produced by burning lignite or sub-bituminous coal. Some fly ash may have CaO content in excess of 10%. In addition to pozzolanic properties, class C fly ash also possesses cementations properties.

3. METHODOLOGY:

The crude used in the production of HRM is centrifuged to appropriate particle size and since the crude is selectively mined for particle size distribution, the particle size distribution of HRM is consistent from lot to lot. The centrifuged product goes through impurity removal steps such as magnetic separation and chemical bleaching to facilitate a consistently white color HRM product. The HRM undergoes optimal thermal treatment in a calciner such that the product exhibits the same maximum pozzolanic activity. Metakaolin is produced by heat-treating kaolin, a natural, finely divided, aluminosiliceous mineral, which is found in abundance in North America in Georgia, South Carolina, and Saskatchewan. Heating to 1200 to 1650°F (650-900°C) alters its structure, producing a highly reactive supplementary cementations material (SCM) that is widely available for use in concrete Construction. ASTM C618 and AASHTO M 295 classify metakaolin as a Class N (or natural) pozzolan. Because it is produced under controlled conditions, its composition (typically 50 to 55% SiO₂ and 40 to 45% Al₂O₃), white appearance, and performance are relatively consistent. Due to its high surface area and high reactivity, relatively small addition rates of metakaolin—typically 10% or less by weight of cement—produce relatively large

increases in strength, impermeability, and durability, while its light color gives it an aesthetic advantage over other SCMs.



Fig.3.1. Self-consolidating concrete using metakaolin.

4. EXPERIMENTAL RESULTS:

Common river sand is expensive due to excessive cost of transportation from natural sources. Also large-scale depletion of these sources creates environmental problems. As environmental transportation and other constraints make the availability and use of river sand less attractive, a substitute or replacement product for concrete industry needs to be found. River sand is most commonly used fine aggregate in the production of concrete poses the problem of acute shortage in many areas. Whose continued use has started posing serious problems with respect to its availability, cost and environmental impact. In such a situation the Quarry rock dust can be an economic alternative to the river sand. Quarry Rock Dust can be defined as residue, tailing or other non-volatile waste material after the extraction and processing of rocks to form fine particles less than 4.75mm.

The concrete mixes had 0%,5%,10% & 15% of Meta kaolin & Fly Ash with partial replacement of cement. After final setting of cubes, the cube moulds were removed and cubes were kept in water tank for curing up to 7days & 28 days. All 48 beam specimen

size 750mmx150mm x150mm were casted with optimum compressive strength for the specific mix in single lift and consolidated using tamping rods. After setting, the beams were kept for curing in water tank. Average of three cubes is taken for compressive strength and average of three beams were taken for flexural strength.

Mix Description	Cement	Sand	Aggregate	Water	MK+FA
M20					
0%	383	735	1103	192	-
5%	363.85	735	1103	192	19.15
10%	344.70	735	1103	192	38.30
15%	325.55	735	1103	192	57.45
M25					
0%	426.66	721.46	1082.18	213	-
5%	405.33	721.46	1082.18	213	21.33
10%	384	721.46	1082.18	213	42.66
15%	362.66	721.46	1082.18	213	64

Fig.4.1. Results analysis.




Fig. (b) Compressive Strength for M20 Grade Concrete

Fig.4.2. Strength Results.




Fig. (e) Flexural Strength for M25 Grade Concrete

Fig.4.3. Flexural strength results.

5. CONCLUSION:

Plain concrete may be a brittle material and fails suddenly. Addition of Metakaoline & fly ash to concrete changes its brittle mode of failure into a additional ductile one and

improves the concrete plasticity. The compressive strength and flexural strength of concrete will increase with Metakaoline fly ash content. It's adjusted to 15 August 1945 replacement if we tend to replace cement by quite 15 August 1945 strength starts reducing. Thus it invariably preferred to USAe Metakaoline & fly ash with 100% replacement of cement and it provides us higher result. Cement replacement up to 13% with metakaolin leads to increase in compressive strength for M-35 grade of concrete. From 17% there is decrease in compressive strength for 3, 7 and 28 days of curing period. The optimum dose of metakaolin for achieving higher compressive strength is 13%. Metakaolin increases the compressive strength of concrete more than 10%. In mixes blended with high percentage of metakaolin, the water demand will be more because of fineness of metakaolin. To maintain workability of concrete at construction site, use of super plasticizers becomes necessary. By effective usage of Metakaolin in optimum percentage in concrete may make concrete economic and environmental friendly.

REFERENCES:

- [1]. Ali Ergun (2011), "Effects of the usage of diatomite and waste marble powder as partial replacement of cement on the mechanical properties of concrete", *Construction and Building Materials*, 25(2), pp 806812.
- [2]. A. Oner , S. Akyuzb, R. Yildiza,(2004)"An experimental study on strength development of concrete containing fly ash and optimum usage of fly ash in concrete" *Cement and Concrete Research* , Vol.35, Issue 6, pp 11651171
- [3]. Bhatti, JI., J Gajda, PE., Botha, F. and MM Bryant, PG. 2006. Utilization of Discarded Fly Ash as a Raw Material in the Production of Portland cement. *Journal of ASTM International*, Vol. 3, No. 10.
- [4]. D.L.Venkatesh Babu, S.C. Natesan, "Studies on Strength and Durability Characteristics of High Performance Silica Fume Concrete", *Proceedings of the INCONTEST 2003*, pp.262 – 267, September 2003.
- [5]. Gopalakrishna, S., Rajamane, N.P., Neelamegam, M., Peter, J.A. and Dattatreya, J.K. 2001. Effect of partial replacement of cement with fly ash on the strength and durability of HPC. *The Indian Concrete Journal*, pp. 335- 341.
- [6]. Subramani, T. "Experimental Investigations on Coir Fibre Reinforced Bituminous Mixes" *International Journal of Engineering Research and Applications*, Vol.2, Issue.3, pp 1794-1804, 2012.
- [7]. Subramani,T, Krishnan.S. And Kumaresan.P.K., Study on Exixting Traffic condition in Salem City and Identify the Transport facility improvement projects, *International Journal of Applied Engineering Research IJAER*, Vol.7,No.7, Pp 717 – 726, 2012.
- [8]. Subramani.T, Sharmila.S, "Prediction of Deflection and Stresses of Laminated Composite Plate with Artificial Neural Network Aid", *International Journal of Modern Engineering Research*, Volume 4, Issue 6 (Version 1), pp 51 -58, 2014.